CCGT CUTTING DATA

KENNEDY®



80º RHOMBIC TYPE

				Material	P			M		K		N	S	H
					Non-alloy steel <25 HRc	Low alloy steel 25-35 HRc	High alloy steel, Tool steel 35-45 HRc	Ferritic / Martensitic Stainless steel	Austenitic Stainless steel	Grey Cast iron	Nodular Cast iron	Aluminium & Non-ferrous material	Heat Resistant and Super Alloys	Hard materials <55 HRc
Order Code	Insert	f_n (mm/rev)	a_p (mm)	VDI	1-5	6-9	10-11	12-13	14	15-16	17-20	21-30	31-37	38-41
KEN1200891L	CCGT060202-N ALU TURNING INSERT	0.02 - 0.15	0.1 - 2.0	v_C (m/min)	-	-	-	-	-	-	-	250 - 800	-	-
KEN1200891M	CCGT060204-N ALU TURNING INSERT	0.05 - 0.15	0.5 - 2.0		-	-	-	-	-	-	-	250 - 800	-	-
KEN1200891N	CCGT09T302-N ALU TURNING INSERT	0.02 - 0.08	0.5 - 1.0		-	-	-	-	-	-	-	250 - 800	-	-
KEN1200891P	CCGT09T304-N ALU TURNING INSERT	0.05 - 0.25	0.5 - 2.0		-	-	-	-	-	-	-	250 - 800	-	-
KEN1200891Q	CCGT09T308-N ALU TURNING INSERT	0.10 - 0.35	1.0 - 3.0		-	-	-	-	-	-	-	250 - 800	-	-

All recommendations are based on ideal machining conditions. Adjustments may need to be made according to your set-up.
The recommendations for speeds, feeds and other parameters presented in this chart are nominal recommendations and should be considered only as good starting points.

Cromwell Group Ltd, Leicester, LE18 2FS, England, **Tel:** 0800 338 877, **Email:** contactus@cromwell.co.uk, **Website:** www.cromwell.co.uk