DUPONT™ PROSHIELD® 20

TECHNICAL DATA SHEET

CAT III

T5

T6

EN 1073-2

EN 1149-5



PRODUCT INFORMATION

DuPont™ ProShield® 20 Blue. Hooded coverall. Stitched external seams. Elasticated wrists, ankles and face. Elasticated waist (stitched-in). Zipper flap. Blue.

ATTRIBUTES

Full Part Number	PBCHF5SBU00
Fabric/Materials	ProShield® 20
Design	Hooded coverall with elastics
Seam	Stitched (external)
Color	Blue
Other Colors	White
Sizes	SM, MD, LG, XL, 2X, 3X
Quantity/Box	50 per box, individually packed.

FEATURES

- Certified according to Regulation (EU) 2016/425
- Chemical protective clothing, Category III, Type 5 and 6
- EN 1073-2 (protection against radioactive contamination)
- Antistatic treatment (EN 1149-5) - on inside
- Stitched external seams
- Nylon zipper with flap

SIZETABLE

PRODUCT SIZE	ARTICLE NUMBER	ADDITIONAL INFO
SM	D15338174	
MD	D15338185	
LG	D15338191	
XL	D15338209	
2XL	D15338211	
3XL	D15338227	

PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Abrasion Resistance [7]	EN 530 Method 2	>10 cycles	1/6 [1]
Basis Weight	DIN EN ISO 536	43 g/m^2	N/A
Colour	N/A	Blue	N/A
Exposure to high Temperature	N/A	Melting point ~165 °C	N/A
Flex Cracking Resistance [7]	EN ISO 7854 Method B	>1000 cycles	1/6 [1]
Puncture Resistance	EN 863	>5 N	1/6 [1]
Resistance to water penetration	DIN EN 20811	3 kPa	N/A
Surface Resistance at RH 25%, inside [7]	EN 1149-1	< 2,5 • 10^9 Ohm	N/A

DUPONT™ PROSHIELD® 20

TECHNICAL DATA SHEET

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Surface Resistance at RH 25%, outside [7]	EN 1149-1	< 2,5 • 10^9 Ohm	N/A
Tensile Strength (MD)	DIN EN ISO 13934-1	>30 N	1/6 [1]
Tensile Strength (XD)	DIN EN ISO 13934-1	>30 N	1/6 [1]
Trapezoidal Tear Resistance (MD)	EN ISO 9073-4	>10 N	1/6 [1]
Trapezoidal Tear Resistance (XD)	EN ISO 9073-4	>10 N	1/6 [1]

1 According to EN 14325 | 2 According to EN 14126 | 3 According to EN 1073-2 | 4 According to EN 14116 | 12 According to EN 11612 | 5 Front Tyvek ® / Back | 6 Based on test according to ASTM D-572 | 7 See Instructions for Use for further information, limitations and warnings | > Larger than | < Smaller than | N/A Not Applicable | STD DEV Standard Deviation |

GARMENT PERFORMANCE

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Nominal protection factor [7]	EN 1073-2	>5	1/3 [3]
Seam Strength	EN ISO 13935-2	>50 N	2/6 [1]
Shelf Life [7]	N/A	3 years [6]	N/A
Type 5: Inward Leakage [11]	EN ISO 13982-2	14 %	N/A
Type 5: Inward Leakage of Airborne Solid Particulates	EN ISO 13982-2	Pass [7]	N/A
Type 6: Resistance to Penetration by Liquids (Low Level Spray Test)	EN ISO 17491-4, Method A	Pass	N/A

1 According to EN 14325 | 3 According to EN 1073-2 | 12 According to EN 11612 | 13 According to EN 11611 | 5 Front Tyvek ® / Back | 6 Based on test according to ASTM D-572 | 7 See Instructions for Use for further information, limitations and warnings | 11 Based on the average of 10 suits, 3 activities, 3 probes | > Larger than | < Smaller than | N/A Not Applicable | * Based on lowest single value |

PENETRATION AND REPELLENCY

PROPERTY	TEST METHOD	TYPICAL RESULT	EN
Repellency to Liquids, Sodium Hydroxide (10%)	EN ISO 6530	>80 %	1/3 [1]
Repellency to Liquids, Sulphuric Acid (30%)	EN ISO 6530	>95 %	3/3 [1]
Resistance to Penetration by Liquids, Sodium Hydroxide (10%)	EN ISO 6530	<5 %	2/3 [1]
Resistance to Penetration by Liquids, Sulphuric Acid (30%)	EN ISO 6530	<5 %	2/3 [1]

1 According to EN 14325 | > Larger than | < Smaller than |

WARNING

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.

This garment and/or fabric are not flame resistant and should not be used around heat, open flame, sparks or in potentially flammable environments.

DuPont™ SafeSPEC™ - We're here to help

Our powerful web-based tool can assist you with finding the appropriate DuPont garments for chemical, controlled environment, thermal and mechanical hazards.



DuPont Personal Protection SafeSPEC™

DuPont Personal Protection

@DuPontPPE

DuPont Personal Protection

CREATED ON: APRIL 11, 2022

© 2022 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™,℠ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.