Machine Translated by Google

Technical sheet
Reference: EXTRATEX WHITE

TECHNICAL DATA

Production method	Spunlace
Composition	Cellulose 60% Polypropylene 40% without binder
Color	Blanc
Weight	± 65 gr/m²
Thickness	± 0,32 mm
Elasticity	96.1% (CD) 54.9% (MD)
Elongation	39.5 N/5cm (CD) 65.8 N/5cm (MD)
Absorption time	50mm/30s
Absorption capacity	5.3ml/g

FEATURES :

- ÿ Hygienic
- ÿ Poor teddy bear
- ÿ Silicone free ÿ
- Wet & dry use
- ÿ Very solid
- ÿ Without binder
- ÿ New fibers
- ÿ Very absorbent
- ÿ **Food contact certificate**



PACKAGING:



Folded in box
Ref EXTRATEX.A/B
PACK OF 10 BAGS OF
44 FTS – 38 X 30 CM
PALLET OF 64 PACKAGES



Dispenser box **Ref**
EXTRATEX.WM/B
BRAGBOX DE 2X160 FTS
42 X35 CM
PALLET OF 80 PACKAGES



Wipe-Pack
Réf EXTRATEX.RFL/B
PACK OF 5 CARTRIDGES
160 FTS 42 X35 CM
PALLET OF 32 PACKAGES



Pre-cut reel **Ref**
EXTRATEX.R/B
1 REEL OF 950 FTS
38 X 40 CM
PALLET OF 24 COILS



Reel in dispenser box
Ref EXTRATEX.PROB/B
DISTR BOX 1 COIL
FROM 390 FTS – 38 X30 CM
PALETTE DE72 BTES

APPLICATIONS :



Aerospace Automotive | Industry Micro-industry | Two | Mechanical | Medical

This data is informative and without commitment. Ets COMPAS cannot be held responsible for any use of this information. These are not specifications but typical characteristics.
The safety data sheet is available on request, except in exceptional circumstances. The characteristics of the products may change when used with products of other types. Any information is subject to change.
modified without prior notice.

74 RUE VERNOUILLET-CS30050-51721 REIMS CEDEX
Winter : 03.26.85.20.84 – Fax : 03.26.85.66.40 – Email : info@compas-alain.fr