TNMG CUTTING DATA

KENNEDY®



60° TRIANGULAR TYPE

				Material	P			M		K		N	S	H
					Non-alloy steel <25 HRc	Low alloy steel 25-35 HRc	High alloy steel, Tool steel 35-45 HRc	Ferritic / Martensitic Stainless steel	Austenitic Stainless steel	Grey Cast iron	Nodular Cast iron	Aluminium & Non-ferrous material	Heat Resistant and Super Alloys	Hard materials <55 HRc
Order Code	Insert	f_n (mm/rev)	a_p (mm)	VDI	1-5	6-9	10-11	12-13	14	15-16	17-20	21-30	31-37	38-41
KEN1203864N	TNMG160404-F C25PM TURNING INSERT	0.05 - 0.25	0.5 - 2.5	v_c (m/min)	150 - 350	90 - 300	70 - 250	120 - 220	50 - 180	-	-	-	-	-
KEN1203864P	TNMG160408-F C25PM TURNING INSERT	0.05 - 0.25	1.0 - 2.5		150 - 350	90 - 300	70 - 250	120 - 220	50 - 180	-	-	-	-	-
KEN1203864Q	TNMG160404-M C25PM TURNING INSERT	0.20 - 0.40	0.5 - 3.0		150 - 350	90 - 300	70 - 250	120 - 220	50 - 180	-	-	-	-	-
KEN1203864R	TNMG160408-M C25PM TURNING INSERT	0.20 - 0.40	1.0 - 3.0		150 - 350	90 - 300	70 - 250	120 - 220	50 - 180	-	-	-	-	-
KEN1203864T	TNMG160412-M C25PM TURNING INSERT	0.20 - 0.40	1.5 - 3.0		150 - 350	90 - 300	70 - 250	120 - 220	50 - 180	-	-	-	-	-
KEN1203864U	TNMG160408-R C25PM TURNING INSERT	0.30 - 0.40	1.0 - 5.0		150 - 350	90 - 300	70 - 250	120 - 220	50 - 180	-	-	-	-	-
KEN1203864V	TNMG160412-R C25PM TURNING INSERT	0.30 - 0.50	1.5 - 4.0		150 - 350	90 - 300	70 - 250	120 - 220	50 - 180	-	-	-	-	-

All recommendations are based on ideal machining conditions. Adjustments may need to be made according to your set-up.
The recommendations for speeds, feeds and other parameters presented in this chart are nominal recommendations and should be considered only as good starting points.

Cromwell Group Ltd, Leicester, LE18 2FS, England, **Tel:** 0800 338 877, **Email:** contactus@cromwell.co.uk, **Website:** www.cromwell.co.uk